THE MARGINAL ADAPTATION OF DIFFERENT ZIRCONIA REINFORCED CERAMIC SYSTEMS: A SYSTEMATIC REVIEW

Rakan Yousef Alrashdan^{1*}, Ahmed Sultan Alharbi¹, Anas Mohamed Baghareeb¹,
Hamad Suliman Alatiah¹, Khaled Saeed Alqahtani¹, Zaki Fakiha²

1. *Dental Interns, College of Dentistry, Riyadh Elm University, Riyadh, Saudi Arabia.*
2. *Department of Prosthodontics, College of Dentistry, Riyadh Elm University, Riyadh, Saudi Arabia. Department of Prosthodontics, College of Dentistry, Riyadh Elm University, Riyadh, Saudi Arabia.*

ARTICLE INFO

Received:

10 Nov 2020

Received in revised form:

24 Dec 2020

Accepted:

24 Dec 2020

Available online:

28 Dec 2020

Keywords: Marginal accuracy, Marginal fit, Marginal gap, Marginal discrepancy, Fitting accuracy, Zirconia crown

ABSTRACT

Purpose: This study aimed to review the published literature examining the accuracy of the marginal fit of the zirconia crown and comparing the marginal adaptation between various systems to identify which of them would achieve better marginal conformity. **Materials and Methods:** A literature review for articles published in the PubMed and Scopus databases was undertaken in February 2020, utilizing explicitly determining inclusion and exclusion criteria. A total of 560 publications were identified, and 330 omitted after screening the title and abstract. After a full-text study, another 214 publications were removed, allowing 16 articles to be used in the final review. The fit refers to the mean marginal gaps in the sample, and the precision is the fit minus the pre-set spacer. **Result:** The overall mean fit values of Zirconia systems were 67µm, and the accuracy was calculated to be 36µm, which is in the clinically desirable range. **Conclusion:** All the Zirconia systems considered in this study produced marginal discrepancy in the clinically desirable range.

Copyright © 2013 - All Rights Reserved - Pharmacophore

To Cite This Article: Alrashdan R K, Alharbi A S, Baghareeb A M, Alatiah H S, Alqahtani K S, Fakiha Z. (2020), "The Marginal Adaptation of Different Zirconia Reinforced Ceramic Systems: A Systematic Review", *Pharmacophore*, 11(6), 157-164.

Introduction

In recent decades, increasing demand from patients for natural-appearing dental restorations has led to the evolution of all ceramic materials with enhanced mechanical characteristics that have better durability. These are currently substituting traditional metal-ceramic restorations. Further, CAD/CAM technology development makes it possible for making such materials. [1–3] Since introducing the CAD/CAM technology in the 1980s computer system has been extensively utilized to design, develop, and shape materials into various forms [4–7]. Mormann was credited for introducing commercially designed CAD/CAM (Cerec, Sirona Dental Systems).[8]

Zirconia is considered as one of the materials milled by CAD/CAM. Zirconia is a kind of ceramics that can occur in many forms without a glassy phase. It is in a monoclinic crystalline form at room temperature, which is changed into a tetragonal and cubic crystalline form when it is sintered. The cooling process from cubic to tetragonal leads to an expansion of 2.3% and tetragonal to monoclinic of 4.2%. These expansions result in cracks formation, so there is a need to stabilize the tetragonal form. By adding a small amount of yttria to the zirconia, the most prevalent way of stabilizing the tetragonal phase and maintaining zirconia in a metastable condition at room temperature is achieved, which is called transformation toughening.[9]

Zirconia reinforced ceramics has an excellent aesthetic quality, biocompatibility, and mechanical property. It has mechanical properties of 1200 HV hardness, 900-1200 MPa flexural strength, and fracture toughness of 6-8 MPa. It has higher strength even when tooth preparation volume is small during making a crown. Moreover, compared to gold, zirconia is less costly. [10] However, the dental restoration's long-term clinical success is affected by the mechanical property, aesthetic quality, and biocompatibility, and by fitting the margin. A large marginal gap leads to a crown's failure by dissolving dental cement

Corresponding Author: Rakan Yousef Alrashdan; Department of Prosthodontics, College of Dentistry, Riyadh Elm University, Riyadh, Saudi Arabia.

so quickly that plaques readily accumulate, causing marginal leakage. [11] The marginal gap usually refers to the space between the restoration margin and preparation margin. Microleakage is passing the bacteria, fluids, molecules, or ions between the tooth structure and the restorative material. [12] Factors that affect the crown's fittings such as; fabrication design, place of the margin, quality of the milling machine, milling bur, cement space, and image capturing system that are reported through in vitro and in vivo studies. [13–20]

The marginal adaptation of dental restorations has been proven to be one of the significant factors causing secondary caries and changing the composition of subgingival microflora that contribute to periodontal disease onset. The clinically permissible marginal adaptation for the dental restoration was reported to range between 17 to 120 μm . [21, 22] Therefore, chamfer and shoulder margins were suggested to make accurate anatomic contour crowns. [23]

Destructive and non-destructive techniques can measure the marginal gap of the restorations. They can be checked clinically using a mirror, probe, and appropriate illumination and magnification. Radiograph and epoxy resin replica using light and scanning electron microscopy are considered as indirect methods. The prepared tooth can be cross-sectioned and evaluated directly to assess the cement space. Modern micro-computed tomography (micro-CT) is employed as a non-destructive method of measuring the marginal gap.

The marginal space of the crowns fabricated from various Zirconia systems differs across studies. It is necessary to review the literature on the marginal space of the zirconia crowns and compare the marginal fit among different systems. Hence this study aimed to review the published literature examining the accuracy of the marginal fit of the zirconia crown and comparing the marginal adaptation between various systems to identify which of them would achieve a better marginal fit.

Materials and Methods

Ethical Approval: The proposal of the study was submitted to Riyadh Elm University's research center, and Institutional review board approval was obtained (FUGRP/2020/150/98/97).

Research Strategy

In the present study, the research was carried out in February 2020 in PubMed and Scopus databases. The research question is, "In abutment teeth, which zirconia system is more accurate in the marginal adaptation?" The PECO is P= abutment teeth. E= one zirconia system. C= other zirconia systems. O= accuracy in marginal adaptation. The research is limited to English-language and peer-reviewed articles published from 2010 until 2020. The following combination of keywords used: ("marginal accuracy," "marginal fit," "marginal gap," "marginal discrepancy," "fitting accuracy," and "zirconia crown"). Titles and abstracts were examined to identify articles that fulfill the inclusion criteria designed for this review. The criteria involved studies evaluating marginal adaptation of zirconia crowns through clear experimental protocols, retrospective, and prospective studies.

Inclusion Criteria

- Language (English)
- Studies of single tooth-supported prostheses or artificial teeth
- The fit assessment described
- Measurement techniques described
- Material (Zirconia)
- Pre-set cement spacer described
- Chamfer or shoulder preparations
- Exclusion Criteria:
 - Studies not meeting all inclusion criteria
 - Studies of implant-supported prostheses
 - Studies measuring fit after ceramic veneering
 - Studies where internal adjustments were made before a fit assessment
 - Studies using subjective tactile sensation

Selection of Studies

The titles and abstracts were reviewed from the studies found in the search described above, considering the inclusion criteria. After selection, the full texts of the studies were acquired. The full-text publications were screened according to the inclusion and exclusion criteria, and 16 studies were included in the review (Figure 1, Table 1). The data collected from the studies included: Author, Year, in vivo/vitro, abutment teeth, Restoration type, Restoration material, number of specimens per group, Preparation type, Cement spacer, Impression type, Scanner, CAD software, CAM machine, Fit assessment method, number of measuring points per abutment, and Marginal gap.

Figure 1: Search Strategy of the Systematic Review

Table 1. Overview of the Included Studies and their Setting Parameters and Results

Authors	System	Imp	Abutment	Evaluation	Spacer	N	F. L	Fit	SD ±	ACC
Hamza et al. [24]	In Coris TZI	Dig	PM	DM	50 µm	6	SH	89.30	2.30	39.30
	Ceramill Zolid							69.40	7.10	19.40
	Zenostar zirconia							75.10	8.20	25.10
	Prettau zirconia Zirkonzahn							72.80	8.90	22.80
	Bruxzir solid zirconia							77.30	11.40	27.30
Riccitiello et al. [25]	Katana zirconia	Conv	PM	MCT	30 µm	15	C	66.00	32.33	36
Habib et al. [26]	Ceramill Motion 2	Dig	M	DM	20 µm	12	C	31.30	15.10	11.30
	Wieland ivoclar							42.33	16.90	22.33
	Cerec Incoris TZI							36.55	17.80	16.55
	Zirkonzahn							44.83	28.70	24.83
	Cad4dent							31.36	19.60	11.36
Hamid Jalali et al. [27]	Cercon	Conv	PM	DM	30 µm	24	narrow SH	71.00	16.00	41
							round SH	80.00	10.00	50
Tariq F. Alghazzawi et al. [28]	Zahnfabrik	Conv	M	S	30 µm	30	SH	36.00	14.00	6
Rafael Schlögel Cunali et al. [29]	Ceramill Motion 2	Dig	M	SR	20 µm	20	C	77.90	12.21	57.90
								68.73	8.86	48.73
	Cerec incoris TZI			MCT				77.83	16.13	57.83
Rocio Ortega et	Nobel Procera	Conv	PM	S	50 µm	40	C	74.83	6.84	54.83
								41.09	7.45	41.09

al. [30]	Lava 3M Zircon							49.48	10.91	49.48
	VITA In-Ceram							65.63	34.59	15.63
Sibel Cetik et al. [31]	Ceramill Motion 2	Conv Dig	M T	S	45µm	60	SH C	C-S 79.0 C-C 101.4 D-S 53.70 D-C 84.90	C-S 39.93 C-C 17.17 D-S 24.01 D-C 24.01	C-S 34 C-C 56.40 D-S 8.70 D-C 39.90
Balaji N Rajan et al. [32]	CERAMILL motion	Dig	M T	S	40 µm	20	SH	83.00	6.77	43
	InCoris TZI							68.00	1.77	28
Min-Kyung Ji et al. [33]	- Zirkonzahn	Dig	PM T	DM	30 µm	48	SH C	118.8	78.20	88.80
	-ZENOSTAR®ZR							40.50	41.50	10.50
Syed Rashid Habib et al. [26]	Ceramill Motion 2	Dig	M T	S	30 µm	100	Deep C	46.93	13.50	6.93
	Wieland, Ivoclar							56.38	30.14	26.38
	Cerec, inCoris TZI							81.75	11.71	51.75
	Prettau Zirconia, Zirkonzahn							101.7	35.56	71.65
	Cad4dent							75.47	46.67	45.47
Ediz Kale et al. [15]	Zenostar	Dig	M	DM	Cement space 40 µm	48	SH	41.00	38.00	1
		CBCT						44.00	42.00	4
		3D						60.00	58.00	20
Raúl Euán et al. [34]	Lava™ 3M ESPE	Conv	M	DM	Cement space 20 µm	20	SH	59.83	11.28	39.83
							C	76.97	7.55	56.97
Lorena Oliveira et al. [35]	Metoxit	Dig	M T	SR	10 µm	10	C	59.20	14.30	49.20
		Conv						71.10	19.10	61.10
		Dig on cast						87	31	77
Syed Rashid Habib et al. [36]	CERCON	Dig	M	DM	30 µm	40	SH	199.5	40.72	169.50
							C	214.5	44.85	184.46
Shoko Miura et al. [37]	Cercon Smart Ceramics System	Conv	M T	SR	30 µm	15	cervical SH	70	30	40
							round SH 0.2	80	30	50
							round SH 0.5	80	40	50

Dig: Digital, Conv: Conventional, M: Molar, PM: Premolar, S: Section Technique, MCT: Micro-CT, SR: Silicon Replica Technique, DM: Digital Microscope, 3D: 3D scan technique, SH: Shoulder finish line, C: Chamfer finish line, T: Typodont, ACC=Accuracy

Table 2. Overview of the intraoral scanners (IOS), CAD software, CAM machine, and zirconia materials used in the studies.

IOS System	CAD Software	CAM Machine	Zirconia Material
Ceramill Map400 [29]	Cercon Art[36]	Cercon Brain[36]	CERAMILL Motion25
Cerec inLab [29,32]	Dentsply Sirona[29]	Dentsply Sirona33	CERAMILL Motion233
Cercon Eye [36]	3Shape software 27	3Shape software27	Ceramill Zolid34
3Shape Trios [26,31,35]	Ceramill 33	Ceramill (Ceramill (motion)[29,32]	Wieland, Ivoclar20,22
S600 ARTI	Cerec [32]	Cerec blanks (in coris TZI) 25,[33]	Cerec InCoris
(Zirkonzahn) [33]	ZirkonzahnArchiv software[33]	Milling machine (Zirkonzahn) [32]	TZISirona[24,26,29,32,38]
ZENO TEC® System	Dental Designer; Wieland[33]	3shape D250[33,35]	Zenostar Ivoclar[15,24,33]
[33]	inCoris Zi33	inCoris Zi33	Bruxzir (10AN)[24]
3D laboratory	Trios 3Shape22	Cercon® brain[37]	Katana Kuraray[25]

scanner[15] Optical Lava™ Scan[34] Ceramill scanner [37] 3Shape D700 [35] N/S [24,38]	Cercon® art[37] Optical Lava™ [34] Cares System Straumann[25] N/S[15,24,26,38]	Lava™ Form[34] MCXL DentsplySirona[24,38] Ceramill(Ceramill motion2) 34 Weiland34 Zirkonzhan34 S1 VHF machine34 Cares System Straumann[25] N/S11,20	Zirkonzahn22,25,[33],33,34 Cad4dent Nacera[26,39] Lava 3M[30,34] Cercon Dentsply Sirona[27,36,37] Zahnfabrik VITA[28] Nobel Procera[30] VITA In-Ceram[30] Metoxit[35]
N/S: not specified; Note: Some of the studies used the addition silicone impression material[21,23–27,30,32]			

Statistical Analysis

The descriptive data are shown as numbers and frequencies. The fit was the mean of marginal gaps in the studies and accuracy was obtained by subtracting fit from the pre-set spacer. Mean values were calculated, resulting from the weighted individual group mean value and the number of test specimens per-group.

Results

The sixteen studies included in the analysis for this review presented a single crown. Four different fit measuring techniques were used: silicone replica technique (three results), sectioning technique (five results), digital microscope (seven results), and Micro-CT technique (Two results) (Table 1). The scanners, CAD software, CAM machines, and zirconia materials are described in (Table 2). Eight of the results had a conventional impression, and ten of them were based on digital techniques. The total mean value of all systems was 67 µm, and the accuracy is 36 µm, which was within the acceptable clinical range.

Discussion

The study's purpose was to review the published literature investigating the accuracy of the marginal fit of a zirconia crown and comparing the marginal adaptation between different systems. According to McLean et al. (1971), the clinically permissible marginal fit is within 120 µm. [21] In an earlier review on the fit of CAD/CAM restorations, published in 2014, the marginal gaps ranged from 39 to 201 µm. [40] These results support the findings of the present study. Our study was mainly based on literature published between 2010 and 2020, and the marginal fit ranged from 31 to 214 µm. A previous study recommended using chamfer and shoulder margins to make the exact anatomic contour of crowns. The mean fit of chamfer and shoulder finish lines are 69 µm and 72 µm, respectively. It was concluded that the marginal fit of zirconia copings with either shoulder or chamfer finish line shows no significant differences. One of the limitations of this study was the lack of standardization to compare conventional impression techniques with the intraoral scanner. Some studies reported that the intraoral digital scanning provided a lower mean gap value than conventional impression and gypsum cast scans. It can be assumed that one of the factors that contributed to decreased marginal discrepancies in some systems is the prostheses were set to the correct position without any friction against the abutments as the correct positioning of the prosthesis requires more cement space. So, the marginal discrepancy is affected by the cement space. In our review, die spacer values ranged between 10 µm-50 µm, the mean marginal fit was 72 µm and 77µm, and the accuracy was 62 µm and 27 µm, respectively. Additional studies are necessary to investigate the optimal cement space required for lower marginal discrepancies within clinically acceptable ranges.

Processing devices are distinguishable by milling axis numbers: 3-axis devices, 4-axis devices, and 5-axis devices. It has been reported that the five-axis dry milling CAM produces better marginal accuracy but takes more time. [24] The highest marginal discrepancy was recorded in group Incoris TZI, which was milled with the MXCL milling machine with a 4-axis motion. It explains the significant difference between Incoris TZI and other systems included in the study. Another critical factor in determining the marginal adaptation is the balance between the shrinkage of pre-sintering blanks and the final sintered zirconia. According to an earlier review, a short sintering time had no effect on zirconia coping's marginal fit. [41] Hence different porcelain-veneering techniques that might lead to changes in zirconia copings' marginal fit were introduced within the dental ceramics. [42] A comparison accuracy of the fit of zirconia-based prostheses fabricated by two CAD/CAM systems, including layering, press-over, and CAD-on techniques, was performed. The results indicated important alterations in all three techniques; however, these alterations were in the range of clinically permissible marginal adaptation. The changes were smallest using the press-over technique and significant compared with the conventional layering technique. About marginal fit, evaluating the zirconia coping was more reliable than on veneered zirconia to determine the system fabrication precision. In the literature, it is mentioned that the cementation techniques may influence the marginal fit due to the variation in cement material viscosity as well as seating forces. Moreover, there is a considerable debate whether using a resin or conventional glass ionomer cement in zirconia crowns. The universal resin cement showed good precision performances irrespective of the restorative material.

Four different fit measuring techniques were used: silicone replica technique, sectioning technique, digital microscope, and Micro-CT technique. Incoris TZI has a marginal gap of 78, 69, 89, and 75 μm , respectively. With the limitations of other factors in this study, the least marginal gap was observed in the sectioning technique. According to the presented results, the Cercon system showed the highest marginal discrepancy (Fit 114 μm ; Accuracy 84 μm), and Zahnfabrik is the least (Fit 36 μm ; Accuracy 6 μm). These study findings may be related to differences in evaluation methodologies such as microscopes, microscope magnification, measurement location, number, or luting agents. However, some studies compared only marginal discrepancy values at two points of zirconia-based prostheses. It is difficult to infer that these values represent the complete accuracy for the fit of the prosthesis. More precise and meaningful conclusions will be drawn if marginal discrepancy values are compared in many points. All specimens produced in-vitro studies were examined under ideal conditions that may not simulate the oral condition.

Conclusion

Within the study's limitations, it can be concluded that all the Zirconia systems considered in this study produced marginal discrepancy within the clinically desirable range. However, the Cercon system recorded the highest marginal discrepancy, and Zahnfabrik was the least. The marginal fit of zirconia copings with either shoulder or chamfer finish line did not significantly differ in marginal discrepancy. Further, reviews and meta-analyses concerning the internal adaptation, marginal gap, and the optimal cement space of crowns fabricated by various zirconia systems are recommended.

References

1. Zarone F, Russo S, Sorrentino R. From porcelain-fused-to-metal to zirconia: clinical and experimental considerations. *Dental materials*. 2011 Jan 1;27(1):83-96. doi:10.1016/j.dental.2010.10.024.
2. Raigrodski AJ, Hillstead MB, Meng GK, Chung KH. Survival and complications of zirconia-based fixed dental prostheses: a systematic review. *The Journal of prosthetic dentistry*. 2012 Mar 1;107(3):170-7. doi:10.1016/S0022-3913(12)60051-1.
3. Biscaro L, Bonfiglioli R, Soattin M, Vigolo P. An in vivo evaluation of fit of zirconium-oxide based ceramic single crowns, generated with two CAD/CAM systems, in comparison to metal ceramic single crowns. *Journal of Prosthodontics: Implant, Esthetic and Reconstructive Dentistry*. 2013 Jan;22(1):36-41. doi:10.1111/j.1532-849X.2012.00907.x.
4. Tleuzhanova GK, Sarzhanova GB, Joldanova DK, Eskzinova ZA, Assanova DN. The role of IT technologies in the formation of students leadership. *Journal of Advanced Pharmacy Education & Research* | Apr-Jun. 2019;9(2).
5. Ibrahim S, Azhar AS, Ather AS, Ahsan AS, Muneer AS, Kaleem AS. Backache: Association with Stature, Posture and Work-Station Ergonomics in Information Technology Professionals-An Analytical Study. *International Journal of Pharmaceutical Research & Allied Sciences*. 2019 Apr 1;8(2).
6. Bakhir VM, Pogorelov A.G. Universal Electrochemical Technology for Environmental Protection. *International Journal of Pharmaceutical Research & Allied Sciences*. 2018 Jan 1;7(1).
7. Kubanov SI, Nuzhnaya CV, Mishvelov AE, Litvinov MS, Povetkin SN. Development of 3D Bioprinting Technology Using Modified Natural and Synthetic Hydrogels for Engineering Construction of Organs. *Int. j. pharm. phytopharm. res.* 2019;9(5):37-42.
8. Mormann WH. Chairside computer-aided direct ceramic inlays. *Quintessence Int.* 1989;20:329-39.
9. Tan Y, Zhang J, Chen P, Zhu Z, Wu S, Tian Z. Zirconia-strengthened yttria ceramics for plasma chamber applications. *Ceramics International*. 2020 Nov 12.
10. Filser F, Kocher P, Weibel F, Luthy H, Scharer P, Gauckler LJ. Reliability and strength of all-ceramic dental restorations fabricated by direct ceramic machining (DCM). *International journal of computerized dentistry*. 2001 Apr;4(2):89-106.
11. Felton DA, Kanoy BE, Bayne SA, Wirthman GP. Effect of in vivo crown margin discrepancies on periodontal health. *The Journal of Prosthetic Dentistry*. 1991 Mar 1;65(3):357-64. doi:10.1016/0022-3913(91)90225-1.
12. Taylor MJ, Lynch E. Microleakage. *Journal of dentistry*. 1992 Feb 1;20(1):3-10. doi:10.1016/0300-5712(92)90002-T.
13. Kokubo Y, Ohkubo C, Tsumita M, Miyashita A, Vult von Steyern P, Fukushima S. Clinical marginal and internal gaps of Procera AllCeram crowns. *Journal of oral rehabilitation*. 2005 Jul;32(7):526-30. doi:10.1111/j.1365-2842.2005.01458.x.
14. Falahchai M, Hemmati YB, Asli HN, Emadi I. Marginal gap of monolithic zirconia endocrowns fabricated by using digital scanning and conventional impressions. *The Journal of prosthetic dentistry*. 2020 Nov 13.
15. Kale E, Cilli M, Özçelik TB, Yilmaz B. Marginal fit of CAD-CAM monolithic zirconia crowns fabricated by using cone beam computed tomography scans. *The Journal of prosthetic dentistry*. 2020 May 1;123(5):731-7. doi:10.1016/j.prosdent.2019.05.029.

16. Mangano FG, Margiani B, Solop I, Latuta N, Admakin O. An Experimental Strategy for Capturing the Margins of Prepared Single Teeth with an Intraoral Scanner: A Prospective Clinical Study on 30 Patients. *International Journal of Environmental Research and Public Health*. 2020 Jan;17(2):392.
17. Saker S, Özcan M. Marginal discrepancy and load to fracture of monolithic zirconia laminate veneers: The effect of preparation design and sintering protocol. *Dental Materials Journal*. 2020.
18. Sampaio CS, Garcés GA, Kolakarnprasert N, Atria PJ, Giannini M, Hirata R. External marginal gap evaluation of different resin-filling techniques for class II Restorations—A micro-CT and SEM Analysis. *Operative dentistry*. 2020 Mar 27.
19. Wu Y, Lv G, Wu S, Zu W, Zhang Y. Clinical Contrastive Analysis on the Marginal Fit of the Planting Crowns and Bridges of Metal Porcelain and Zirconium Dioxide All Porcelain. *Acta Microscopica*. 2020 Jul 1;29(5).
20. Mathivadani V, Kommi V, Arivarasu L. Marginal Integrity Around Bonded Fixed Prosthesis After Instrumentation With Subgingival Scalers And Curettage-A Review. *European Journal of Molecular & Clinical Medicine*. 2020 Dec 2;7(1):3175-81.
21. McLean JW. The estimation of cement film thickness by an in vivo technique. *Br dent j*. 1971;131:107-11. doi:10.1038/sj.bdj.4802708.
22. Martínez-Rus F, Suárez MJ, Rivera B, Pradies G. Evaluation of the absolute marginal discrepancy of zirconia-based ceramic copings. *The Journal of prosthetic dentistry*. 2011 Feb 1;105(2):108-14. doi:10.1016/S0022-3913(11)60009-7.
23. Pera P, Gilodi S, Bassi F, Carossa S. In vitro marginal adaptation of alumina porcelain ceramic crowns. *The Journal of prosthetic dentistry*. 1994 Dec 1;72(6):585-90. doi:10.1016/0022-3913(94)90289-5.
24. Hamza TA, Sherif RM. In vitro evaluation of marginal discrepancy of monolithic zirconia restorations fabricated with different CAD-CAM systems. *The Journal of prosthetic dentistry*. 2017 Jun 1;117(6):762-6. doi:10.1016/j.prosdent.2016.09.011.
25. Riccitiello F, Amato M, Leone R, Spagnuolo G, Sorrentino R. In vitro evaluation of the marginal fit and internal adaptation of zirconia and lithium disilicate single crowns: micro-CT comparison between different manufacturing procedures. *The open dentistry journal*. 2018;12:160.
26. Habib SR, Al Otaibi AK. Comparison between five CAD/CAM systems for fit of zirconia copings. *Quintessence International*. 2018 Jun 1;49(6). doi:10.3290/j.qi.a40354.
27. Jalali H, Sadighpour L, Miri A, Shamshiri AR. Comparison of marginal fit and fracture strength of a CAD/CAM zirconia crown with two preparation designs. *Journal of dentistry (Tehran, Iran)*. 2015 Dec;12(12):874.
28. Alghazzawi TF, Liu PR, Essig ME. The effect of different fabrication steps on the marginal adaptation of two types of glass-infiltrated ceramic crown copings fabricated by CAD/CAM technology. *Journal of Prosthodontics: Implant, Esthetic and Reconstructive Dentistry*. 2012 Apr;21(3):167-72. doi:10.1111/j.1532-849X.2011.00803.x.
29. Cunali RS, Saab RC, Correr GM, Cunha LF, Ornaghi BP, Ritter AV, Gonzaga CC. Marginal and internal adaptation of zirconia crowns: a comparative study of assessment methods. *Brazilian Dental Journal*. 2017 Aug;28(4):467-73. doi:10.1590/0103-6440201601531.
30. Ortega R, Gonzalo E, Gomez-Polo M, Suárez MJ. Marginal and Internal Discrepancies of Posterior Zirconia-Based Crowns Fabricated with Three Different CAD/CAM Systems Versus Metal-Ceramic. *International Journal of Prosthodontics*. 2015 Sep 1;28(5). doi:10.11607/ijp.4359.
31. Cetik S, Bahrami B, Fossoyeux I, Atash R. Adaptation of zirconia crowns created by conventional versus optical impression: in vitro study. *The Journal of Advanced Prosthodontics*. 2017 Jun 1;9(3):208-16. doi:10.4047/jap.2017.9.3.208.
32. Rajan BN, Jayaraman S, Kandhasamy B, Rajakumaran I. Evaluation of marginal fit and internal adaptation of zirconia copings fabricated by two CAD-CAM systems: An in vitro study. *The Journal of the Indian Prosthodontic Society*. 2015 Apr;15(2):173. doi:10.4103/0972-4052.159970.
33. Ji MK, Park JH, Park SW, Yun KD, Oh GJ, Lim HP. Evaluation of marginal fit of 2 CAD-CAM anatomic contour zirconia crown systems and lithium disilicate glass-ceramic crown. *The journal of advanced prosthodontics*. 2015 Aug 1;7(4):271-7. doi:10.4047/jap.2015.7.4.271.
34. Euán R, Figueras-Álvarez O, Cabratosa-Termes J, Brufau-de Barberà M, Gomes-Azevedo S. Comparison of the marginal adaptation of zirconium dioxide crowns in preparations with two different finish lines. *Journal of Prosthodontics: Implant, Esthetic and Reconstructive Dentistry*. 2012 Jun;21(4):291-5. doi:10.1111/j.1532-849X.2011.00831.x.
35. Pedroche LO, Bernardes SR, Leao MP, KINTOPP CC, Correr GM, Ornaghi BP, Gonzaga CC. Marginal and internal fit of zirconia copings obtained using different digital scanning methods. *Brazilian oral research*. 2016;30(1). doi:10.1590/1807-3107BOR-2016.vol30.0113.
36. Habib SR, Al Ajmi MG, Al Dhafyan M, Jomah A, Abualsaud H, Almashali M. Effect of margin designs on the marginal adaptation of zirconia copings. *Acta stomatologica Croatica*. 2017 Sep 26;51(3):179-87. doi:10.15644/asc51/3/1.
37. Miura S, Inagaki R, Kasahara S, Yoda M. Fit of zirconia all-ceramic crowns with different cervical margin designs, before and after porcelain firing and glazing. *Dental materials journal*. 2014 Jul 30;2013-84. doi:10.4012/dmj.2013-284.

38. Habib SR. Digital microscopic evaluation of vertical marginal discrepancies of CAD/CAM fabricated zirconia cores. *Biomedical Engineering/Biomedizinische Technik*. 2019 Apr 24;64(2):207-14. doi:10.1515/bmt-2017-0234.
39. Khaledi AA, Vojdani M, Farzin M, Pirouzi S, Orandi S. The effect of sintering time on the marginal fit of zirconia copings. *Journal of Prosthodontics*. 2019 Jan;28(1):e285-9. doi:10.1111/jopr.12731.
40. Boitelle P, Mawussi B, Tapie L, Fromentin O. A systematic review of CAD/CAM fit restoration evaluations. *Journal of oral rehabilitation*. 2014 Nov;41(11):853-74. doi:10.1111/joor.12205.
41. Contrepois M, Soenen A, Bartala M, Laviolle O. Marginal adaptation of ceramic crowns: a systematic review. *The Journal of prosthetic dentistry*. 2013 Dec 1;110(6):447-54. doi:10.1016/j.prosdent.2013.08.003.
42. Torabi K, Vojdani M, Giti R, Taghva M, Pardis S. The effect of various veneering techniques on the marginal fit of zirconia copings. *The Journal of Advanced Prosthodontics*. 2015 Jun 1;7(3):233-9. doi:10.4047/jap.2015.7.3.233.